



TEL: 0161 330 6644
 FAX: 0161 330 4437

CT-165 cleaner plus

GRANITE - SANDSTONE - BRICK

TERRA COTTA

Aggressive version of CT-160
For stubborn brick work and heavy stains
MASKING OF WINDOWS REQUIRED

PRODUCT: CT-165 Plus

APPLICATION: REMOVAL OF DIRT, SOOT and GENERAL GRIME FROM

BRICK*
 SANDSTONE
 TERRA - COTTA*
 UNPOLISHED GRANITE

Care needs to be taken with these grades of Masonry. Dilution will be necessary. 1:1 with water.

GENERAL: SRL's CT-165 Plus can be used to effectively clean a wide range of masonry. Instructions for proper use are explained on the reverse of this product data sheet. Care has to be taken when using this product since some masonry is more sensitive than other grades. In all cases it is necessary to pre-wet the surface to prevent over absorption into the stone.



The product can be diluted to suit each application - masonry type. For Sandstone and Granite (unpolished) CT165 can be used neat, undiluted. However, with Terra Cotta and Brickwork the product will have to be diluted 1:1 with water. If you have doubt about the suitability of this product for a particular application it is prudent to conduct a small trial in a discrete corner of the masonry to satisfy ones doubt. Contact time on Sandstone/Granite is approx 1 - 2 minutes. It will be necessary to "mask" widow panes. It is prudent to conduct a small trial / test in order to establish the suitability of this product with each application.

Following the contact time CT-165 must be removed with high pressure water jet @ approx. 1500 psi.

CHEMICAL PROPERTIES:

Composition: Blend of Acids
 Surfactants

Form: Liquid

Density: 1.2 kg/l

pH: 0

Flash point: -





TEL: 0161 330 6644
FAX: 0161 330 4437

CT-165 cleaner plus

GRANITE - SANDSTONE - BRICK


TERRA COTTA

Aggressive version of CT-160
For stubborn brick work and heavy stains
MASKING OF WINDOWS REQUIRED


Page 2 of 2

HOW TO USE:


Warning: All non masonry materials need to be shielded from contact with this product. It is prudent to conduct individual trial test first. It will be necessary to screen the public and other contractors from any splash from this product. Once the product is airborne there is danger it may be carried and deposited on passing vehicles or parked cars causing damage to paintwork.



2. Acid may need to be diluted to suit the application. Dilution up to 1:4 is possible. 1:1 water is typical.



3. Recommended contact time will vary depending on temperature and type of masonry. Typical times 1 - 2 mins



4. Rinse off the acid using high pressure water jet. Ensure suitable personnel protection is maintained even during rinse down stages.

PACKAGING:

CT-165 is supplied in 25, 200 and 1000lt containers. All containers are UN certified and carry correct labelling.

STORAGE:

CT-165 should be stored indoors at room temperature. Containers must be kept in an upright position and the caps properly sealed and away from unauthorised persons.

SAFETY FIRST:

As always when using chemicals proper protective clothing should/must be worn; rubber boots, protective gloves, rubber apron and face visor. Respiratory equipment will be required in confined spaces.

ENVIRONMENT:

The waste produced after pickling needs to be collected and neutralised before entering the public sewage system. SRL offer neutralising products to assist in this cause. Where possible practical collect all waste product, embank with sand and deposit in plastic container. Dispose of properly by the local environmental regulations.

Information given in this leaflet may be subject to alteration without notice
care has been taken to ensure that the contents of this publication are accurate but Stainless Restoration Ltd do not accept responsibility for error or for information which is found to be misleading. Suggestions for or descriptions of the end use or application of products or methods of working are for information only and the company accept no liability in respect thereof. Before using products supplied or manufactured by the company the customer should satisfy himself of their suitability. If further assistance is required, the company which has access to extensive research facilities, will often be willing to help.

Stainless Restoration Ltd
Unit 2, Boodle street
Ashton-Under-Lyne, Manchester OL6 8NF
Tel: 0161 330 6644 Fax: 0161 330 4437 www.stainrest.com